



CERNE

ISSN: 0104-7760

ISSN: 2317-6342

UFLA - Universidade Federal de Lavras

Freitas, Thaís Pereira; Oliveira, José Tarcísio da Silva;  
Vidaurre, Graziela Baptista; Rodrigues, Brunela Pollastrelli  
ENVIRONMENTAL EFFECT ON CHEMICAL COMPOSITION  
OF EUCALYPTUS CLONES WOOD FOR PULP PRODUCTION

CERNE, vol. 24, no. 3, -, 2018, pp. 219-224

UFLA - Universidade Federal de Lavras

DOI: 10.1590/01047760201824032558

Available in: <http://www.redalyc.org/articulo.oa?id=74460167007>

- How to cite
- Complete issue
- More information about this article
- Journal's homepage in [redalyc.org](http://redalyc.org)

UAEM [redalyc.org](http://redalyc.org)

Scientific Information System Redalyc

Network of Scientific Journals from Latin America and the Caribbean, Spain and Portugal

Project academic non-profit, developed under the open access initiative



**Keywords:**  
Wood quality  
Genetic material  
Growth site

**Historic:**  
Received 12/04/2018  
Accepted 28/08/2018

**\*Correspondence:**  
thais\_pfreitas@yahoo.com.br

Thaís Pereira Freitas<sup>1+</sup>, José Tarcísio da Silva Oliveira<sup>2</sup>, Graziela Baptista Vidaurre<sup>2</sup>, Brunela Pollastreli Rodrigues<sup>2</sup>

## ENVIRONMENTAL EFFECT ON CHEMICAL COMPOSITION OF EUCALYPTUS CLONES WOOD FOR PULP PRODUCTION

FREITAS, T. P.; OLIVEIRA, J. T. S.; VIDAURRE, G. B.; RODRIGUES, B. P. Environmental effect on chemical composition of eucalyptus clones wood for pulp production. **CERNE**, v. 24, n. 3, p. 219-224, 2018.

### HIGHLIGHTS

The extractive content was the characteristic that suffered the highest site effect.

The S/G ratio was considered to be the most stable characteristic to environmental change.

There is a significant variation between the values of S/G ratio among different clones.

The holocellulose (%) was the second characteristic lowest influenced by the environment.

### ABSTRACT

This study aimed to evaluate the environmental effect on the wood chemical composition of *Eucalyptus grandis* x *Eucalyptus urophylla* clones for pulp production. Seven clones of 6.5 years old were evaluated. The clones were planted in two growing sites, Nova Almeida – Espírito Santo and Posto da Mata – Bahia, established in 3 x 3 m spacing. Five trees were selected from each clone and discs were removed from five different positions equidistant from the trunk and at diameter at breast height (DBH) height. Two wedge from opposite sides were obtained from the discs. A chemical analysis was performed with a sample composed of all the wedges of each tree in order to determine extractive contents, lignin, holocellulose, carbohydrates and the ratio among syringyl (S) and guaiacyl (G) lignin substructures (S/G) per tree. The S/G ratio was considered to be the most stable characteristic to environmental change, followed by the holocellulose content, which was considered the second least characteristic influenced by the growth site. Most of the studied clones presented a statistical difference between the growing site for the wood extractive content, in contrast to the total carbohydrates content that was highlighted by presenting values which were little influenced by the genetic material and the growth site.

<sup>1</sup> Federal University of Viçosa, Viçosa, Minas Gerais, Brazil

<sup>2</sup> Federal University of Espírito Santo, Jerônimo Monteiro, Espírito Santo, Brazil

## INTRODUCTION

Some *Eucalyptus* species have become increasingly important in pulp production in different parts of the world such as in southern Europe, South America, South Africa and Australia. The interbreeding between species is a reality in Brazil and has become more common since hybrids are being used in huge commercial plantation areas (Gominho et al., 2001). On a world scale, *Eucalyptus* plantations also stands out as it is estimated that 20 million hectares are planted and distributed in tropical, subtropical and temperate zones (Rejmánek and Richardson, 2011).

Nowadays, the *Eucalyptus grandis* x *Eucalyptus urophylla* hybrid provides most of the wood that is used for hardwood pulp companies in Brazil, since this interspecific combination results in vigorous trees with fast initial growth, resistance to cancrees caused by a type of fungus and high wood quality, being highly adapted to the pulp and paper industry, and presenting high yields and high pulp quality (Gonzalez et al., 2014).

Wood properties are a result of the interaction between the genetic tree potential and the environmental conditions where it grows, and the environment influences on wood properties is being studied by many authors (Brito, 1985). Some countries, such as Brazil, have a wide range edaphoclimatic conditions, therefore in order to guarantee a more homogenous feedstock production, it is important that the clones suffer the least influence possible from their growth site on the wood technological characteristics (Gouvea et al., 2012).

The growing knowledge of the impact of raw-material properties on pulp quality has led to research on wood quality parameters and to their integration with selection traits in the improvement programs (Miranda and Pereira, 2002).

One of the wood characteristics that are used to determine wood quality in the pulping process are its chemical proprieties. The plant cell is constituted from macromolecular components, which are the primary or structural constituents of the cell wall formed by cellulose, hemicellulose, and lignin; and the secondary or non-structural constituents are the extractives and the inorganic compounds (Carvalho et al., 2009). The variations that occur in the cellulose pulp quality are mainly caused by the change in the chemical quantities and composition of the raw-material which result from different factors, including the site quality, harvest period, geographic location from the plant, climate, age and species/clones (Silvério et al., 2008; Bikovens et al., 2013).

The chemical composition of woods to be used in pulp production is crucial, because it has a direct relation

with the pulping process efficiency. Gomide et al. (2010) showed the lignin and extractives content importance in wood such as the quality standards from the *Eucalyptus* to the cellulose production, since they have significant effects on the kraft pulping process and with good correlations during the process, since the higher the lignin and extractive content in the wood, the higher the reagent consumption and the lower the pulping yield.

In this context, this work aims to evaluate the environmental effect on the wood chemical composition of different *Eucalyptus grandis* x *Eucalyptus urophylla* hybrid clones for pulp production.

## MATERIAL AND METHODS

### Experimental material and local sample

The wood from the study came from seven *Eucalyptus grandis* x *Eucalyptus urophylla* hybrid clones from clonal test plots established in 3 x 3 m spacing with an age 6.5 years in planting areas of the Fibria Celulose S.A. company in two locations. One location was in Nova Almeida/Espirito Santo, Brazil (20°3'7" S and 40°14'28" W) and the other at Posto da Mata/Bahia, Brazil (17° 53' 44" S and 39° 34' 2" W).

Information regarding rainfall and temperature were taken from the historical data from the years in which the planting occurred (2007-2014) and was obtained from the stations that compose the climate monitoring system of the Fibria Celulose S.A. company. Edaphoclimatic information is listed in Table I.

The tree sampling of the seven clones was performed in the same stand in each region. Five trees were used for each clone and site, and one disk was taken from each tree from the diameter at breast height (DBH, i.e. diameter at 1.30m shoot extension) and another from the positions at 0, 25, 50, 75 and 100% of the tree's commercial height.

### Chemical characterization

One wedge was then removed from each disc of the different positions with a radial angle of 20° for the chemical analyses in order to obtain a composite sample with the amount of material of each disk proportional to its position, representing the whole tree.

The wedges were reduced into wood chips which were homogenized and air-dried, then transformed into sawdust in a Willey mill according to the Technical Association of the Pulp and Paper Industry - T 257 om-92 (TAPPI, 1992).

**TABLE 1** Height (H), stem diameter (SD), leaf area (LA), shoot dry mass (SDM) and root system dry mass (RSDM) of *Khaya ivorensis* clonal seedlings, 120 days after staking.

Location	P (mm·year <sup>-1</sup> )	T (°C)	Soil type	Soil texture	OM1	OM2	AWC	Altitude	Relief
NA	1247.3	23.3	Typical Yellow Argisol	Medium/ clayey	2.7	2.3	260	43.0	Smooth undulated
PM	1455.6	24.3	Dystrophic Yellow Argisol to prominent	Sandy/ medium/ clayey	1.0	0.9	157	33.3	Flat

The extractive analyses were performed according to TAPPI T204 om 97(1992). From the sawdust samples,  $2.0 \pm 0.001$ g were taken moisture-free and arranged in a glass crucible with porosity 2. The sawdust samples were submitted to acetone extraction for a period of 5h. A mix with solvent and the extractive solution from the extraction was put into a lab oven at  $103 \pm 2^\circ\text{C}$  to evaporate the solvent. When dried, the samples were weighed and the extractive content was obtained by the weight difference.

The lignin content (Klason) was determined according to TAPPI T222 om-06 (1992), but with a few changes described by Coleman et al. (2008). After the extractive removal,  $\pm 0.2$ g of the sample was put inside a glass bottle, their masses recorded, and then the samples were hydrolyzed with three mL of 72% sulfuric acid ( $\text{H}_2\text{SO}_4$ ) for 2 hours. The solution was then manually homogenized with a glass stick every 10 minutes. Then, 112 mL of distilled water was added to each bottle, and they were sealed and autoclaved for 1 hour at  $121^\circ\text{C}$ . The solution was filtered, and the insoluble lignin content (Klason) was determined by weight difference.

The soluble lignin content was obtained from the liquid remaining from filtering the insoluble lignin and analyzed in a UV spectrophotometer, in which 0.1 mL of the liquid containing the soluble lignin was diluted in 1.5 mL of 4% sulfuric acid ( $\text{H}_2\text{SO}_4$ ). The absorbance of the filtrate was read at the wavelength of 205 nm. The soluble lignin content was determined according to Equation 1, where SL is the Soluble lignin content (%) and A205 is the absorbance for the 205m wave.

$$SL = \left( \left( \frac{A_{205}}{110} \right) \cdot 1840 \right) \cdot 100 \quad [1]$$

The total lignin content consisted of the soluble and insoluble fractions together, and the holocellulose was determined by the difference between the initial mass and amount of extractives from the total lignin.

The carbohydrates content in the wood was determined by taking 1 mL from the remaining liquid

from the insoluble lignin filtration. This was subsequently analyzed by high-performance liquid chromatography (Dionex DX-500, Dionex, CA) equipped with an ionic change PAI column (Dionex), an amperometric detector pulsed with a gold electrode, and a Dionex AS.

The sugars concentration (arabinose, galactose, glucose, xylose, mannose and rhamnose) were determined by the external standard method when using the commercial analytical standards. A differential refraction detector was used for the monosaccharides detection and a computer program determined the peak integrations.

The monolignol composition was performed in duplicate using the thioacidolysis method (2 mL of  $0.25 \text{ mg} \cdot \text{mL}^{-1}$  of  $\text{CH}_2\text{Cl}_2$ ) by gas chromatography (GC) according to a method described by Robinson and Mansfield (2009).

Gas chromatography was performed on a Thermo Scientific-TRACE GC 1310 equipped with an AI 1310 injector and a TG-5MS column. The GC method used an injection volume of 2 mL, one injector of initial temperature of  $250^\circ\text{C}$ , and detector temperature of  $270^\circ\text{C}$ . The initial temperature was  $130^\circ\text{C}$  (maintained for 3 minutes) and increased at a rate of  $3^\circ\text{C}$  per minute to  $260^\circ\text{C}$ , and maintained for 5 min.

The extractive content was determined in the Wood Science Laboratory of the Federal University of Espirito Santo, Brazil. Moreover, the carbohydrate, lignin, holocellulose and ratio among syringyl (S) and guaiacyl (G) lignin substructures (S/G) were determined in the laboratory of the Wood Science Department at the University of British Columbia, Vancouver, Canada.

## Data analysis

The experiment was conducted in an entirely randomized design with a  $2 \times 7$  factorial arrangement; the factors were the clones (seven levels) and the sites (two levels), with five repetitions. When the interaction effect between the clone and the site were significant by the variance analysis on the F-test ( $p \leq 0.05$ ), it showed the existence of dependency between the considered

factor (clone and site), therefore the interaction analysis and comparison between means by the Scott-Knott test ( $p \leq 0.05$ ) were performed.

## RESULTS AND DISCUSSION

The soluble lignin content was the only studied variable that showed no significant clone x site interaction, but it showed a significant statistical difference at 5% probability for the clone and local factors separately, and the comparison between the averages is presented in Table 2. It is observed that the highest values were obtained for this variable in Nova Almeida - ES.

**TABLE 2** Mean soluble lignin content values per clone and site for the *E. grandis* x *E. urophylla* hybrid at 6.5 years of age.

Variable	Site		Clones						
	NA	PM	1	2	3	4	5	6	7
SL	4.06 a	3.70 b	3.86 c	4.13 b	3.49 c	4.72 a	3.57 c	3.69 c	3.74 c

NA = Nova Almeida - ES; PM = Posto da Mata - BA; SL = soluble lignin (%). Means followed by the same letter do not differ from each other by the Scott-Knott test ( $p > 0.05$ ).

The clone x site interaction was significant at 5% probability for all the other studied characteristics. Thus, an interaction analysis and a mean comparison were performed (Table 3).

The S/G ratio was the chemical composition that had the lowest environmental influence, however, there is a significant variation between the values among the different genetic materials, where the minimum relation was 2.32 for the clone 3 and the maximum 3.86 for the clone 4, both in Posto da Mata/BA.

Results inside this range were also obtained by Alves et al. (2011) for *E. grandis* x *E. urophylla*, which

obtained an S/G ratio of 2.9 for 7-year old clones from an implantation in Southern Bahia. Barbosa et al. (2008) found an average value of  $2.5 \pm 0.09$  in studying the use of analytical pyrolysis combined with gas chromatography/mass spectrometry (Py-GC/MS) to determine the syringyl/guaiacyl ratio (S/G) in 7-year old *E. grandis* x *E. urophylla* lignins.

Those results also corroborate the values obtained by Nunes et al. (2010) and Gouvêa et al. (2011) who found mean values between 2.78 - 2.86 and 2.59 - 3.03 for S/G ratio of 3-year old eucalyptus clones from four different regions.

According to Gomide et al. (2005), the syringyl lignin had a less condensed structure due to it being more easily dissolved during the kraft pulping process, and as a consequence are more favorable to delignification by cooking liquor. Nevertheless, this relationship is still controversial, because while some researchers encounter good correlation in some species between the lower consumption of reagents (alkali) and increase in pulp yield, others dispute those results.

Thus, the clone selection for pulp production is important to not only look at the wood lignin content, but also its chemical structure that affects the process yield, since the higher the S/G ratio, the more favorable the delignification is, thereby allowing a lower alkali use in the kraft pulping and consequently increasing the yield. However, the ideal wood for kraft pulp production is one containing low lignin and a high S/G ratio (Gomes et al., 2008).

The chemical composition suffering more environmental influence was the extractives content, presenting statistically significant difference for most clones (1, 3, 4, 6 and 7). Mean values of 2.68 and 2.35%

**TABLE 3** Mean values and multiple comparison test for the chemical composition of *E. grandis* x *E. urophylla* hybrid at 6.5 years of age at different growth sites.

Variables	Site	Clones						
		1	2	3	4	5	6	7
S/G	NA	3.17 b A	3.53 a A	2.34 c A	3.50 a B	2.54 c A	3.14 b A	3.12 b A
	PM	2.84 c A	3.32 b A	2.32 d A	3.86 a A	2.39 d A	2.96 c A	2.83 c A
EXT	NA	2.77 a B	1.89 b A	3.42 a A	2.86 a A	2.67 a A	3.33 a A	1.82 b B
	PM	3.77 a A	2.05 c A	2.03 c B	0.94 d B	2.45 c A	2.34 c B	2.90 b A
IL	NA	25.67 a A	24.93 a B	26.30 a A	26.14 a A	25.11 a B	25.51 a A	25.97 a B
	PM	26.18 b A	26.24 b A	26.73 a A	25.12 b A	26.82 a A	26.68 a A	27.77 a A
TL	NA	29.81 b A	29.22 b A	29.97 b A	31.10 a A	28.78 b B	29.42 b A	29.77 b B
	PM	29.77 a A	30.20 a A	30.03 a A	29.59 a B	30.29 a A	30.14 a A	31.44 a A
HO	NA	67.42 b A	68.89 a A	66.61 b A	66.04 b B	68.55 a A	67.25 b A	68.41 a A
	PM	66.46 c A	67.75 b A	67.94 b A	69.46 a A	67.27 b A	67.52 b A	65.66 c B
TCA	NA	62.39 a A	62.22 a A	62.77 a A	60.92 a B	62.85 a A	61.99 a B	61.27 a A
	PM	61.99 a A	62.98 a A	63.12 a A	63.00 a A	63.47 a A	63.87 a A	59.81 b A

NA = Nova Almeida - ES; PM = Posto da Mata - BA; S/G = lignin syringyl: guaiacyl; EXT = extractive (%); IL = insoluble lignin (%); TL = total lignin (%); HOL = Holocellulose (%); TCA = total carbohydrates. Means values followed by the same lowercase letter in the row and upper case in the column do not differ from each other by the Scott-Knott test ( $p > 0.05$ ).

were obtained in Nova Almeida - ES and Posto da Mata - BA, respectively. Approximate values were found by Zanuncio et al. (2013), who obtained averages ranging from 2.1 to 2.5% for different thinning regimes in eucalyptus clone forest plantations (*Eucalyptus grandis* x *Eucalyptus urophylla*).

Miranda and Pereira (2002) studied the quality of 9-year old *Eucalyptus globulus* wood planted at three sites, and also verified that extractive content was the characteristic that had the highest variation among the studied properties. Nonetheless, Miranda et al. (2007) evaluated the core, the extractives and the pulp yield of *Eucalyptus globulus* clones grown at two different sites, and found no significant effect of the location or clones on the extractive values.

The total lignin content was encountered at the range of 28.78 (clone 5, Nova Almeida/ES) to 31.44% (clone 7, Posto da Mata/BA). These results corroborate with Gouvea et al. (2012), who also studied the site effect on the technological characteristics of *Eucalyptus* wood and found total lignin content from 27.2 to 30.9%.

The holocellulose content was the second lowest characteristic influenced by the environment, as a statistically significant difference between the sites was only detected in two clones. The holocellulose term comprehends the total polysaccharides content in the wood and is represented by the cellulose fraction together with hemicellulose, which could be up to 80% of the total. It is mainly present in the cellular wall (Gulichsen and Paulapuro, 2000). High contents from these composts are favorable to pulp production; different from extractives and lignin.

The holocellulose content constituted on average 67.60 and 67.44% of the wood mass for the different clones and growth sites in Nova Almeida - ES and Posto da Mata - BA, respectively, ranging from 65.66 to 68.89%. This variation range corroborates with Gomide et al. (2005), who encountered holocellulose content between 64.5 and 70.2% for a eucalyptus clone.

The results from this current study are also in agreement with those obtained by Medeiros et al. (2016) and Segura et al. (2016) who found an average holocellulose content of 66.12 and 68.85% for *E. grandis* x *E. urophylla* wood of 4 and 6 years old, respectively.

The total carbohydrate content evidences a significant statistical difference at 5% for the clone x site interaction, therefore leading to an analysis and mean comparison being performed (Table 2). In Nova Almeida/ES, there was no significant influence on the average carbohydrate content. In relation to the site influence, only the clones 4 and 6 showed a significant difference between the means. In general, it can be observed that

this characteristic was little influenced by the clone and the site, presenting minimum percentage values of 61.27% and maximum of 63.47%.

## CONCLUSIONS

The ratio among syringyl (S) and guaiacyl (G) lignin substructures (S/G) was considered the most stable property to environment changes, while the holocellulose content was the second least influenced by the growth site. The extractive content was the chemical composition that suffered the highest effect from the site. With the exception of the clones 4 and 7, in general, the genetic materials used in this study were considered to be little influenced by the environment, which is an advantage, since it is desired to obtain clones that are more stable to external variations and that can be indicated for different growth sites.

## ACKNOWLEDGEMENTS

To Fibria Celulose S.A. that donated the material. To the *Fundação de Amparo à Pesquisa do Espírito Santo – FAPES*, and the University of British Columbia that made the accomplishment of the Scientific Technical Internship abroad possible.

## REFERENCES

- ALVES I.C.N.; GOMIDE, J.L.; COLODETTE, J.L.; SILVA, H.D. Technological characterization of *Eucalyptus benthamii* wood for kraft pulp production, Brazil. **Ciência Florestal**, Santa Maria, v.21, n.1, p.167-174, 2011.
- BARBOSA L.C.A.; MALTHA C.R.A.; SILVA V.L. Determination of the syringyl/guaiacyl ratio in *Eucalyptus* wood by Pyrolysis-gas Chromatography/mass Spectrometry (PY-GC/MS), Brazil. **Química Nova**, v.31, n.8, p.2035-2041, 2008.
- BIKOVEN O.; ROZE L.; PRANOVICH A.; REUNANEN M.; TELYSHEVA G. Chemical composition of lipophilic extractives from Grey Alder (*Alnus incana*), USA. **BioResources**, v.8, n.1, p.350-357, 2013.
- BRITO J.O. **Influence of fertilizer application on the tree rings characteristics of *P. caribaea* var. *bahamensis***. 1985. 113 p. PhD thesis Universidade de São Paulo, Escola Superior de Agricultura “Luiz de Queiroz”, Piracicaba, Brazil.
- CARVALHO, W.; CANILHA, L.; FERRAZ, A.; MILAGRES, A.M.F. A vision of wood structure, composition and biodegradation, Brazil. **Química Nova**, v.32, n.8, p.2191-2195, 2009.
- COLEMAN H.D.; PARK J.Y.; NAIR R.; CHAPPLE C.; MANSFIELD S.D. RNAi-mediated suppression of p-coumaroyl-CoA 3'-hydroxylase in hybrid poplar impacts lignin deposition and soluble secondary metabolism, USA. **Proceedings of the National Academy of Sciences**, v.105, n.11, p.4501-4506, 2008.



- GOMES, F.J.B.; GOUVÊA, A.F.G.; COLODETTE, J.L.; GOMIDE, J.L.; CARVALHO, A.M.M.L.; TRUGILHO, P.F.; GOMES, C.M.; ROSADO, A.M. Influence of content and S/G relation of the wood lignin on kraft pulping performance, Brazil. **O papel**, v.69, n.12, p.95-105, 2008.
- GOMIDE J.L.; COLODETTE J.L.; OLIVEIRA R.C.; SILVA C.M. Technological characterization of the new generation of *Eucalyptus* clones in Brazil for kraft pulp production, Brazil. **Revista Árvore**, v.29, n.1, p.129-137, 2005.
- GOMIDE J.L.; FANTUZZI NETO H.; REGAZZIA. Analysis of wood quality criteria of eucalyptus wood for kraft pulp production, Brazil. **Revista Árvore**, v.34, n.2, p.339-344, 2010.
- GOMINHO J.; FIGUEIRA J.; RODRIGUES J.C.; PEREIRA H. Within-tree variation of heartwood, extractives and wood density in the eucalypt hybrid urograndis (*Eucalyptus grandis* x *E. urophylla*), USA. **Wood and Fiber Science**, v.33, n.1, p.3-8, 2001.
- GONÇALEZ J.C.; SANTOS, G.L.; SILVA JUNIOR, F.G.; MARTINS I.S.; COSTA J.A. Wood Fiber size and density relationship along the stem of *Eucalyptus urograndis*, Brazil. **Scientia Forestalis**, v.42, n.101 p.81-89, 2014.
- GOUVEA A.F.G.; TRUGILHO P.F.; COLODETTE J.L.; BIANCHI M.L.; SORAGI L.C.; OLIVEIRA A.C. Relationship among wood characteristics and *Eucalyptus* cellulose pulp with the non destructive methods in the living tree, Brazil. **Scientia Forestalis**, v.39, n.90, p.205-220, 2011.
- GOUVEA A.F.G.; GOMES C.M.; MATOS L.M.; SOUZA T.A.; KUMABE F.J.B.; BENITES P.K.R.M. Effect of the site in technological characteristics of *Eucalyptus* wood for kraft pulp production, Brazil. **Ciência da Madeira**, v.3, n.2, p.102-115, 2012.
- GULLICHSEN J.; PAULAPURO H.B. **Papermaking science and technology: forest products chemistry**. Helsinki: FAPET, 2000. 300p.
- MEDEIROS B.L.M.A.; GUIMARÃES JUNIOR J.B.; RIBEIRO M.X.; LISBOA F.J.N.; GUIMARÃES I.L.; PROTÁSIO T.P. Evaluation of physical and chemical properties *Corymbia citriodora* and *Eucalyptus urophylla* x *Eucalyptus grandis* wood, cultured in Piauí, Brazil. **Nativa**, Sinop, v.4, n.6, p.403-407, 2016.
- MIRANDA I.; GOMINHO J.; LOURENCO A.; PEREIRA H. Heartwood, Extractives and Pulp Yield of Three *Eucalyptus globulus* Clones Grown in Two Sites, Australian/New Zealand. **Appita Journal: Journal of the Technical Association of the Australian and New Zealand Pulp and Paper Industry** v.60, n.6, p.485-500, 2007.
- MIRANDA I.; PEREIRA H. Variation of pulpwood quality with provenances and site in *Eucalyptus globulus*, France. **Annals of Forest Science**, v.59, n.3, p.283-291, 2002.
- NUNES C.A.; LIMA C.F.; BARBOSA L.C.A.; COLODETTE J.L.; GOUVEIA A.F.G.; SILVÉRIO F.O. Determination of *Eucalyptus* spp lignin S/G ratio: A comparison between methods. **Bioresource Technology**, v.101, p.4056-4061, 2010.
- REJMÁNEK M.; RICHARDSON D.M. Eucalypts. In: **Encyclopedia of biological invasions**. Simberloff, D, Rejmánek M (Eds.). Berkeley, University of California Press, p. 203-209, 2011.
- ROBINSON A.R.; MANSFIELD S.D. Rapid analysis of poplar lignin monomer composition by a streamlined thioacidolysis procedure and near-infrared reflectance-based prediction modeling, USA. **The Plant Journal**. v.58, n.4, p.706-706, 2009.
- SEGURA, T. E. S.; SANTOS, J. R. S. ; SARTO, C. ; SILVA JR., F. G. . Effect of Kappa Number Variation on Modified Pulping of *Eucalyptus*. **Bioresources**, v.11, p.9842-9855, 2016.
- SILVÉRIO F.O.; BARBOSA L.C.A.; MALTHA C.R.A.; FIDÊNCIO P.H.; CRUZ M.P.; VELOSO D.P.; MILANEZ A.F. Effect of storage time on the composition and content of wood extractives in *Eucalyptus* cultivated in Brazil. **Bioresource Technology**. v.99, n.11, p.4878-4886, 2008.
- TECHNICAL ASSOCIATION OF THE PULP AND PAPER INDUSTRY – TAPPI. **Tappi test methods T 257 om-92: sampling and preparing wood for analysis**. Atlanta: Tappi Technology Park I, 1992.
- ZANUNCIO A.J.V.; COLODETTE J.L.; GOMES F.J.B.; CARNEIRO A.C.O.; VITAL B.R. Chemical composition of Eucalypt wood with different levels of thinning, Brazil. **Ciência Florestal**, v.23, n.4, p.755-760, 2013.