



Revista Argentina de Microbiología

ISSN: 0325-7541

ram@aam.org.ar

Asociación Argentina de Microbiología
Argentina

Guiamet, Patricia; Igareta, Ana; Battistoni, Patricia; Gómez de Saravia, Sandra
Fungi and bacteria in the biodeterioration of archeological fibers. Analysis using different microscopic techniques

Revista Argentina de Microbiología, vol. 46, núm. 4, octubre-diciembre, 2014, pp. 376-377


Asociación Argentina de Microbiología
Buenos Aires, Argentina

Available in: <http://www.redalyc.org/articulo.oa?id=213032862015>

- How to cite
- Complete issue
- More information about this article
- Journal's homepage in redalyc.org

redalyc.org

Scientific Information System
Network of Scientific Journals from Latin America, the Caribbean, Spain and Portugal
Non-profit academic project, developed under the open access initiative



MICROBIOLOGICAL IMAGE

Fungi and bacteria in the biodeterioration of archeological fibers. Analysis using different microscopic techniques

Hongos y bacterias en el biodeterioro de fibras arqueológicas.
Análisis con diferentes técnicas microscópicas

Patricia Guiamet^{a,b}, Ana Igareta^c, Patricia Battistoni^a, Sandra Gómez de Saravia^{a,d,*}

^a Instituto de Investigaciones Fisicoquímicas Teóricas y Aplicadas (INIFTA), Departamento de Química, Facultad de Ciencias Exactas, UNLP, CCT La Plata-CONICET, cc 16 SSuc 4 (1900) La Plata, Argentina

^b Facultad de Ciencias Veterinarias, UNLP, CCT La Plata-CONICET, La Plata, Argentina

^c División Arqueología, Museo de La Plata. FCNyM, UNLP, CCT La Plata-CONICET, La Plata, Argentina

^d Facultad de Ciencias Naturales y Museo, UNLP, CIC, La Plata, Argentina

Received 16 July 2014; accepted 1 Set 2014

Pre and post-Columbian archeological textiles from the Southern Andean area, sheltered in Deposit 25 at La Plata Museum (Fig. 1), were analyzed by Olympus BX51 optical microscopy (OM) (Fig. 2A and 3A), FEI Quanta 200 scanning electron microscopy (SEM) (Figs. 2B and 3C) and Leica SP5 confocal laser scanning microscopy (CLSM) (Fig. 3B) with the aim of studying their biodeterioration³. For over 120 years, these textiles have provided information to archeologists around the world, and it was through the study of many pieces that we now know in detail the characteristics of the material culture of the various groups that inhabited the territory during the national Holocene period. Textiles containing natural fibers, and cotton fabrics can present problems when exposed to unfavorable external conditions. High humidity and temperature and insufficient air circulation result in enhanced growth of microorganisms, especially fungi². Uncontrolled fungi growth leads to the complete deterioration of archeological fibers. Microorganisms such as fungi and bacteria (ie. *Cladosporium* sp. and *Pseudomonas* sp.) (Fig. 3) cause the biodeterioration of cellulose, which



Figure 1 General view of textile No. 60177 at La Plata Museum where foxing spots are observed.

* Corresponding author.

E-mail address: sgomez@inifta.unlp.edu.ar (S. Gómez de Saravia).




Figure 2 Details of textile structure. A. Image from optical microscopy (X10, Bar= 500 µm) and B. image from SEM (X100, Bar= 1 mm).




Figure 3 Biological structures related to the development of hyphae of cellulolytic fungi (*Cladosporium* sp.) and bacteria (*Pseudomonas* sp.) are observed. A. Image from optical microscopy (X100, Bar= 50 µm), B. image from Confocal Laser Microscopy C (Bar= 25 µm) and C. image from SEM (X3500, Bar= 30 µm).

is the main component of natural fibers such as flax and cotton⁴. This leads to loss of strength of the natural fibers, causing odor emission, esthetic damage, the presence of staining, discoloration (foxing) and finally loss of fiber structure⁵, and giving rise to significant losses at economic and cultural levels. Proper storage of textiles susceptible to biodeterioration in special containers under conditions of temperature and relative humidity suitable are effective preventive measures to avoid undesirable results. Essential oils and silver nanoparticles¹, among others, can be used as disinfectants for the surface of archeological fibers, historical objects and archival documents. It is essential that all tasks and strategies used in the preservation of the material be written and documented photographically, so as to keep a record for regularly assessing changes of microorganism activity leading to textile damage.

Acknowledgements

The authors thank the National University of La Plata (UNLP) Incentive Projects 11N 713 and 11X 632, the National

Council of Scientific and Technical Research PIP 0200 (CONICET), and the Scientific Commission Research of Buenos Aires Province (CIC-833/14).

References

1. Gutarowska B, Skora J, Zduniak K, Rembisz D. International analysis of the sensitivity of microorganisms contaminating museums and archives to silver nanoparticles. *Int Biodet Biodegr.* 2012;68:7-17.
2. Lavin P, Gómez de Saravia SG, Guíamet PS. An environmental assessment of biodeterioration in document repositories. *Biofouling.* 2014;30:561-9.
3. Lira Eyzaguirre MP. Análisis científico de fibras arqueológicas. Universidad de Chile. *Conserva.* 2002 6:47-59.
4. Mariani R, Igareta A, Varela G, Gómez de Saravia S, Guíamet P. Entomofauna presente en textiles de colecciones arqueológicas y otros factores de riesgo de biodeterioro. I Congreso Latinoamericano. II Congreso Nacional de Museos Universitarios. 2013. p.1-12.
5. Szostak-Kotowa J. Biodeterioration of textiles. *Int Biodet Biodegr.* 2004;53:165-70.