



Ingeniería e Investigación

ISSN: 0120-5609

revii\_bog@unal.edu.co

Universidad Nacional de Colombia  
Colombia

Zea, Hugo Ricardo  
Nanomaterials: health effects and legislation  
Ingeniería e Investigación, vol. 32, núm. 1, abril, 2012, pp. 36-41  
Universidad Nacional de Colombia  
Bogotá, Colombia

Available in: <http://www.redalyc.org/articulo.oa?id=64323227007>

- How to cite
- Complete issue
- More information about this article
- Journal's homepage in redalyc.org

redalyc.org

Scientific Information System  
Network of Scientific Journals from Latin America, the Caribbean, Spain and Portugal  
Non-profit academic project, developed under the open access initiative

# Nanomaterials: health effects and legislation

## Efectos de los nanomateriales en la salud y su normatividad

Hugo Ricardo Zea<sup>1</sup>

### RESUMEN

La forma como los materiales nanométricos interactúan con sistemas biológicos es poco conocida, y aunque los beneficios de algunos nanomateriales son evidentes también existe la posibilidad de que algunos puedan ser nocivos para la salud y el medio ambiente; sin embargo, la información científica sobre los efectos de los nanomateriales en estos ámbitos es escasa. Este documento hace una breve descripción de los efectos en la salud de los nanomateriales y los desarrollos legislativos concernientes a su regulación.

**Palabras clave:** nanomateriales, efectos sobre la salud, legislación.

### ABSTRACT

The mechanisms by which nanomaterials interact with biological systems is not well understood and although the benefits of some nanomaterials are evident, some offset effects on health and the environment may occur; however, scientific information is scarce. This document gives a brief description of the effects of nanomaterials on health and the current tendencies in developing the pertinent regulations.

**Keywords:** Nanomaterials, health effects, legislation.

Received: September 6th 2011

Accepted: February 27th 2012

### Introduction

The International Organization for Standardization (ISO) defines a nanoobject as being a material having at least one of its three external dimensions in the nanoscale order (from 1 to 100 nm); many products making use of nanomaterials' properties are already available on the market, therefore being in direct contact with and manipulation by consumers. A mass entrance onto the market of products which include nanomaterials in their formulation is expected in the coming years (pharmaceutical products, elements for diagnosis, electronics, production and energy storage) (Lu *et al.*, 2009; Sahaym and Norton, 2008). These new advances' economic impact has been considered in billions of dollars; such impact is estimated at being around 450 billion dollars for 2015 just in the electronics industry (Hullmann, 2007; Kobayashi, 2004; Losch, 2006; Luther *et al.*, 2005). A common challenge for all emerging technologies is to identify potential risks during the early development stages and not at more advanced stages when remediation efforts prevail over prevention procedures.

The mechanisms by which nanometric materials interact with biological systems are not well understood and, although the benefits of some nanomaterials are evident, some of them could be dangerous and risky to human health. Existing knowledge about nanomaterials' toxicity is limited; some studies have been performed to understand potential health risks according to nanomaterials' exposure route (inhalation, skin contact, ingestion), for example, it has been determined that certain types of carbon

nanotubes can cause lung cancer if inhaled (Muller *et al.*, 2005); nevertheless, most of the health risks which nanomaterials could cause are subject to current investigation (Table 1 summarises some of the results).

### Inhalation

Inhalation is the most frequent route for exposure to nanomaterials and the resulting effects are closely related to inhaled material particle size; dispersed particles having an average size smaller than 100 nm have greater toxicity than aggregates of the same nanomaterial (300 to 700 nm) (Canoe *et al.*, 2004; Shvedova *et al.*, 2006). Available information indicates that the percentage of nanometric particles in the 10 to 90 nm range deposited in the pulmonary alveoli increases from 26% to 47% whilst percentage decrease for particles bigger than 100 nm; in terms of particle deposition in the bronchial zone, this percentage decays continuously with increased particle size (Oberdorster *et al.*, 1994). Other studies have established that the effect of inhaled particles not only depends on the amount of inhaled particles but also on their surface area (Driscoll *et al.*, 1997; Oberdorster and Yu, 1999). Human exposure-related literature is scarce due to restrictions on carrying out experimental studies; an important source of information regarding the effects of nanomaterials in human health can be obtained from production units and factories' occupational health reports; e.g. printer ink cartridge factory workers developed severe damage in their lungs by inhaling nanoparticles; analysis of samples taken from the workers' lungs showed pleural granulomas, fluid accumulation and the deposition of particles of about 30 nm, both in pleural membranes and in fluid extracted from lungs.

Studies on rats led to determining that nanoparticles having around 40 nm diameter may lodge in lung walls and migrate to the circulatory system; such particles deposited on the nasal inner tissue

<sup>1</sup> Chemical Engineer, Universidad de América, Colombia. MSc in Chemical Engineering, Universidad Nacional de Colombia, Colombia. PhD in Chemical Engineering, University of New Mexico. Associated Professor Universidad Nacional de Colombia. E-mail: hrzeaz@unal.edu.co

Material	Exposure	Effect	Reference
Titanium dioxide	Inhalation	Lung membrane inflammation	Sager et al., 2008 Warheit et al., 2007 Warheit et al., 2009
SWCNT	Inhalation	Lung membrane inflammation, breathing deficiency, reduction of immunologic capacity	Mercer et al., 2008 Shvedova, et al., 2005 Shvedova et al., 2003
CNT	Inhalation	Lung membrane inflammation, development of malignant cells in lungs walls	Poland et al., 2008 Takagi et al., 2008
Fullerenes	Inhalation	No reported effects	Baker et al., 2008
Iron oxide	Inhalation	Accumulation in the olfactory bulb	Saba et al., 2010
Nickel	Inhalation	Lung membrane inflammation, accumulation in some organs beyond the respiratory system	Ispas, et al., 2009 Kang, et al., 2011
Quantum dot Qdot 655	Skin contact	Epidermis penetration, inflammation of subcutaneous layers	Ryman-Rasmussen et al., 2006)
Quantum dot Qdot 566	Skin contact	Epidermis penetration	Ryman-Rasmussen et al., 2006
CNT	Skin contact	Epidermis inflammation, penetration of cell membrane	Monteiro-Riviere et al., 2005 Murray et al., 2007 Shvedova, et al., 2003
Nickel	Skin contact	Penetration of cell membrane	Ispas et al., 2009
Titanium dioxide	Ingestion	Cytotoxic effects on digestive system cells, modifying DNA molecular structure, damaging effects to liver and small intestine walls	Dybdahl et al., 2003 Moos et al., 2010 Trouiller et al., 2009 Wang et al., 2006 Wang et al., 2007
Zinc oxide	Ingestion	Cytotoxic effect on digestive system cells, modification of DNA molecular structure, growth delay, renal injury and anaemia	Dybdahl et al., 2003 Moos et al., 2010 Trouiller et al., 2009 Wang,et al., 2006, Wang et al., 2007
Vanadium oxide	Ingestion	Cytotoxic effect on digestive system cells, modification of DNA molecular structure	Dybdahl et al., 2003 Moos et al., 2010 Trouiller et al., 2009 Wang et al., 2006 Wang et al., 2007

migrate directly into the brain through the olfactory nerve (Aust *et al.*, 2009; Geyser *et al.*, 2005; Harder *et al.*, 2005; Warheit *et al.*, 2009). Experimental studies on mice have demonstrated that insoluble doses of nanoparticles have a bigger impact on health than equivalent doses of the same material aggregate in larger diameter particles causing pulmonary inflammation, pulmonary membrane damage and tumours (Barlow *et al.*, 2005; Heinrich *et al.*, 1995; Lee *et al.*, 1985; Oberdorster *et al.*, 1992; Oberdorster *et al.*, 1994; Oberdorster and Yu, 1990; Renwick *et al.*, 2004).

Ultra-fine TiO<sub>2</sub> (anatase) particles have been shown to be highly active in terms of pulmonary membrane inflammation; nevertheless, the effect of particles smaller than 2 µm was not established, given individual ultra-fine particles' tendency to become aggregated in the pulmonary membrane (Sager *et al.*, 2008); other reports have concluded that the main incidence for pulmonary tumours caused by inhaling 20 to 300 nm TiO<sub>2</sub> particles has been observed for 20 nm particles (10 mg/m<sup>3</sup> concentration) even if 300 nm particle concentration were 25 times bigger (250 mg/m<sup>3</sup>) (Heinrich *et al.*, 1989; Lee *et al.*, 1986).

Carbon nanotubes (CNT) represent another substance requiring special attention given their large number of applications. Scientific publications have reported granuloma formation and pleural inflammation in rats and mice exposed to CNT-contaminated atmospheres; these results also indicated that once CNT have reached the lungs, their toxicity is higher than that of comparable materials like charcoal and quartz (Lam *et al.*, 2004; Service, 2003; Warheit *et al.*, 2004). Special types of CNT are those constituted by a single wall (SWCNT) which when supplied to mice by inhalation in doses varying from 0.5-2 mg/kg had a high incidence regarding pulmonary membrane inflation, respiratory deficiency, reduced immunological capacity and some cases of pleural fibrosis

during the first 7 days' exposure (Mercer *et al.*, 2008; Shvedova *et al.*, 2005). The same studies led to concluding that SWCNT particles having an average 100 nm diameter did not behave as asbestos particles, as has been hypothesised previously (Takagi *et al.*, 2008); studies published by the US National Institute for Occupational Health and Safety (NIOSH) established that only a small fraction of the CNT present in air are in fact inhaled during breathing (Maynard *et al.*, 2004).

### Skin contact

Skin exposure to nanomaterials essentially takes place during handling and manipulating consumer products formulate to be applied directly to the skin (cosmetics, sun block, topical medicine). The skin is constituted by three layers: the epidermis, dermis and subcutaneous layer. There is also an external layer of dead cells constituting the uppermost section of the epidermis called "stratum corneum" (SC); these dead cells become the skin's first barrier and protection against external agents. Most of the available literature regarding nanomaterials interaction with the skin has been focused on determining whether pharmacological formulations are able to penetrate through the skin. TiO<sub>2</sub> particles are a main component of solar radiation protection products; several studies have demonstrate that TiO<sub>2</sub> micron size particles are able to penetrate the SC but do not cross into the dermis' most inner layers (Lademann *et al.*, 1999); however, particles of the same material in sizes ranging from 5-20 nanometers penetrate all the skin's layers and interact with the immunological system (Hosmer *et al.*).

Additional factors besides those inherent in the properties of nanomaterials in contact with the skin (dose, vehicle, reactivity)

have been considered important variables in determining their effects (skin age, anatomical exposure site, wounds or exposed lacerations, etc.). Experimental evidence has proved that wounded skin facilitates nanomaterial migration into the inner layers, especially at sites of the body where the skin tends to be thin (Hostynek 2003); smaller nanomaterials penetrate deeper into the skin's layer than bigger particles (Mossman and Sesko, 1990). Some studies have suggested that nanomaterials could penetrate the skin during prolonged occupational exposure (Hoet *et al.*, 1999). There is no certainty whether nanomaterial penetration through skin causes detrimental health effects; however, specific studies on mice regarding the application of topical formulations containing SWCNT have caused skin irritation (Fischer *et al.*, 2003). *In vitro* studies using human epithelial cells have demonstrated that both CNT and SWCNT penetrate and damage the cell membrane (Morgan *et al.*, 1988).

### Ingestion

Determining nanomaterials' effects on health regarding the digestive system has become an important issue lately as many processed food products contain nanoscale ingredients in their preparation, besides food becoming contaminated with nanomaterials by coming into contact with surfaces containing them (packaging material, kitchen utensils, etc.). Such nanoparticle materials might be able to accumulate in organs like the kidneys and the liver. Although nanoparticle absorption in the gastrointestinal apparatus is apparently low, health risks due to ingested nanomaterials have still not been clearly determined and are extremely dependent on nanomaterial's inherent characteristics (size, surface structure, chemical composition). Little data is available regarding nanomaterials' toxic or inflammatory potential; it has been reported that vanadium nanometric oxide particles have cytotoxic effects on digestive system cells; similar effects have been reported for zinc oxide nanometric particles (Moos *et al.*, 2010). Some studies on rats and mice have demonstrated damage to DNA molecular structure and high nanoparticle toxicity for several types of materials; the most affected organs have been the liver and small intestine inner walls (Dybdahl *et al.*, 2003). The oral administration of high doses (5 g Zn/kg) of ZnO nanoparticles has caused growth delay during the first days of treatment, accompanied by collateral effects such as renal damage, anaemia and the death of two of the case studies (Wang *et al.*, 2006); the same authors have reported hepatic and renal injuries when oral administration was replicated using TiO<sub>2</sub> nanoparticles (Trouiller *et al.*, 2009; Wang *et al.*, 2007).

### Legislation

The efficacy of any effort to regulate chemical substances is based upon a solid knowledge of the materials covered by such regulation; unfortunately, there is still great uncertainty regarding nanomaterials concerning these materials' potential risks, mainly due to the absence of appropriate standardised tests and procedures for determining such risks. Despite the lack of such knowledge, a lack of specific regulation for characterising the risks involved, health consequences and effects on the environment, some authors have identified three fundamental challenges in creating legislation for regulating nanomaterials: obtaining agreement for defining nanomaterial, determining whether current legislation can be adapted or whether a new regulatory framework must be created and defining whether nanomaterials should be considered as different material from their macroscopic counterpart having the same molecular structure (Chaundry *et al.*, 2006).

Regarding the first challenge, the European organisation in charge of registering, evaluating, authorising and regulating chemical materials (REACH) defines nanomaterial as an insoluble or biopersistent material, intentionally manufactured with one or more of its external dimensions (or incorporated in its internal structure) in the 1 to 100 nm scale (Monica, 2008.). The USA initiative for nanotechnology shares the same definition proposed by REACH; however, it also includes nanomaterials available in nature besides intentionally manufactured ones. Organisations such as the American Chemical Society (ACS) and the International Organisation for Standardisation (ISO) have proposed their own definitions which sometimes come into conflict and emphasise the need for obtaining consensus on a definition leading to creating and implementing appropriate and effective regulation (Boxall *et al.*, 2008; Monica, 2008).

The second challenge is related to determining whether existing regulation can be adapted to nanomaterials' unique characteristics; an important group of regulatory organisations have adopted an incremental approach, assuming that current chemical substances' regulation can be adapted and, in some specific cases, modified to include nanomaterials; nevertheless, some authors have argued that nanomaterials' special characteristics demand new and specific regulation. A possible complication arising from the use of such incremental approach would be the constant implementation and/or regulatory adaptation of addenda, which could make its application troublesome and confusing.

The third challenge concerns defining whether nanomaterials' physical-chemical and toxicological characteristics are equivalent to those of material having the same chemical composition but above the scale defined for nanomaterials. This definition would have a fundamental impact on producers and manufactures fulfilling requirements before marketing any nanomaterial (Chaundry *et al.*, 2006). If nanomaterial is classified as being a substance different from its macroscopic counterpart having the same molecular structure in the USA, then current regulation would require that a producer has a pre-manufacture note (PMN) which must be sent to the Environmental Protection Agency (EPA) before such material is produced in any amount different to that intended for research and development; this PMN must include information about environmental impact and toxicity (Hansen *et al.*, 2008; Hansen SF, 2008). The European Community has decided to assume that nanomaterials are covered by the definition of chemical substances currently approved by REACH, with the following reservation that when an existing chemical substance already being marketed in bulk is introduced on the market in the form of nanomaterial, then the material safety data sheet (MSDS) must be modified to include the specific characteristics of such substance as nanomaterial (Hansen *et al.*, 2008).

Any new regulation must be based upon fundamental principles such as health and environmental protection, innovation and high level of participation of the bodies involved (regulating agencies, research entities, producers, consumers). Toxicological test results must contain degradation, accumulation, as well as recommendations about labour and environmental exposure as minimum information regarding physical-chemical characteristics to ensure the protection of health and the environment. The need to make manufacturers and producers responsible for nanomaterial throughout its whole life-cycle also becomes clear (Hansen and Tickner, 2008).

## Conclusions

Although information related to nanomaterials' effects on health is scarce, an important increase in related scientific literature has been identified. It is clear that nanomaterials can penetrate most of the body's protective membranes and accumulate in diverse organs. Inhalation has been the most studied exposure route whilst the effects of skin contact and ingestion have not received the same detailed research. Overall effects can vary from simple irritation to tumour formation and DNA molecular modification. A special characteristic of nanomaterials is that their toxicity seems to be closely related to their surface area. Future work must concentrate on obtaining a definition of nanomaterial. It must be determined whether current legislation can be adapted or whether a new regulatory framework must be created, and it must be defined whether nanomaterials should be considered as different material from their macroscopic counterparts having the same molecular structure (Chaundry *et al.*, 2006).

## References

- Aust, W., Daum, N., Bloching, M., Armbruster, V., Jung, E., Sprau, C., Muller, M., Boehm, A., Mozet, C., Wichmann, G. and Dietz, A., Risk of Nanoparticles?, *Laryngo-Rhino-Otologie*, Vol. 88, No 3, 2009, pp. 162-166
- Baker, G., Gupta, A., Clark, M., Valenzuela, B., Staska, L., Harbo, S., Pierce, J. and Dill, J., Inhalation toxicity and lung toxicokinetics of C60 fullerene nanoparticles and microparticles. *Toxicol Sci*, Vol. 101, No 1, 2008 pp. 122-31
- Barlow, P., Clouter-Baker, A., Donaldson, K., Maccallum, J. and Stone, V., Carbon black nanoparticles induce type II epithelial cells to release chemotaxins for alveolar macrophages. *Particle and Fibre Toxicology*, Vol. 6, No 1, 2005, pp. 10-11
- Boxall, A., Chaudhry, Q., Sinclair, C., Jones, A., Aitken, R., Jefferson, B. and Watts, C., Current and future predicted environmental exposure to engineered nanoparticles., *York Central Science Laboratory*, Vol. No 2008, pp. 70-90
- Chalupa, D. C., Morrow, P. E., Oberdorster, G., Utell, M. J. and Frampton, M. W., Ultrafine particle deposition in subjects with asthma. *Environmental Health Perspectives*, Vol. 112, No 8, 2004, pp. 879-882
- Chaundry, Q., Blackburn, J., Floyd, P., George, C., Nwaogu, T., Boxall, A. and Aitken, R., A scoping study to identify gaps in environmental regulation for the products and applications of nanotechnologies. . London: Department for Environment, Food and Rural Affairs, Vol. No 2006, pp. 10-21
- Driscoll, K. E., Deyo, L. C., Carter, J. M., Howard, B. W., Hassenbein, D. G. and Bertram, T. A., Effects of particle exposure and particle-elicited inflammatory cells on mutation in rat alveolar epithelial cells. *Carcinogenesis*, Vol. 18, No 2, 1997, pp. 423-430
- Dybdahl, M., Risom, L., Moller, P., Autrup, H., Wallin, H., Vogel, U., Bornholdt, J., Daneshvar, B., Dragsted, L. O., Weimann, A., Poulsen, H. E. and Loft, S., DNA adduct formation and oxidative stress in colon and liver of Big Blue (R) rats after dietary exposure to diesel particles. *Carcinogenesis*, Vol. 24, No 11, 2003, pp. 1759-1766
- Fischer, D., Li, Y. X., Ahlemeyer, B., Kriegelstein, J. and Kissel, T., In vitro cytotoxicity testing of polycations: influence of polymer structure on cell viability and hemolysis. *Biomaterials*, Vol. 24, No 7, 2003, pp. 1121-1131
- Geiser, M., Rothen-Rutishauser, B., Kapp, N., Schurch, S., Kreyling, W., Schulz, H., Semmler, M., Hof, V. I., Heyder, J. and Gehr, P., Ultrafine particles cross cellular membranes by nonphagocytic mechanisms in lungs and in cultured cells. *Environmental Health Perspectives*, Vol. 113, No 11, 2005, pp. 1555-1560
- Hansen, S., Maynard, A., Baun, A. and Tickner, J., Late lessons from early warnings for nanotechnology. *Nature Nanotechnology* Vol. 3, No 2008, pp. 444
- Hansen, S. and Tickner, J., Putting risk-risk tradeoffs in perspective: a response to Graham and Wiener. *Journal of Risk Research*, Vol. 11, No 2008, pp. 475
- Hansen SF, M. E., Kamper A, Borling P, Stuer- Lauridsen F, Baun A., Categorization framework to aid exposure assessment of nanomaterials in consumer products., *Ecotoxicology* Vol. 17, No 2008, pp. 438-447.
- Harder, V., Gilmour, P. S., Lentner, B., Karg, E., Takenaka, S., Ziesenis, A., Stampfl, A., Kodavanti, U. P., Heyder, J. and Schulz, H., Cardiovascular responses in unrestrained WKY rats to inhaled ultrafine carbon particles. *Inhalation Toxicology*, Vol. 17, No 1, 2005, pp. 29-42
- Heinrich, U., Fuhst, R., Rittinghausen, S., Creutzenberg, O., Bellmann, B., Koch, W. and Levsen, K., Chronic inhalation exposure of Wistar rats and 2 different strains of mice to diesel-engine exhaust, carbon-black, and titanium-dioxide. *Inhalation Toxicology*, Vol. 7, No 4, 1995, pp. 533-556
- Heinrich, U., Muhle, H., Hoymann, H. G. and Mermelstein, R., Pulmonary-function changes in rats after chronic and subchronic inhalation exposure to various particulate matter. *Experimental Pathology*, Vol. 37, No 1-4, 1989, pp. 248-252
- Hoet, P. H. M., Gilissen, L. P. L., Leyva, M. and Nemery, B., In vitro cytotoxicity of textile paint components linked to the "Ardystil syndrome". *Toxicological Sciences*, Vol. 52, No 2, 1999, pp. 209-216
- Hosmer, J. M., Shin, S. H., Nornoo, A., Zheng, H. A. and Lopes, L. B., Influence of internal structure and composition of liquid crystalline phases on topical delivery of paclitaxel. *Journal of Pharmaceutical Sciences*, Vol. 100, No 4, pp. 1444-1455
- Hostynek, J. J., Factors determining percutaneous metal absorption. *Food and Chemical Toxicology*, Vol. 41, No 3, 2003, pp. 327-345
- Hullmann, A., Measuring and assessing the development of nanotechnology. *Scientometrics*, Vol. 70, No 3, 2007, pp. 739-758
- Ispas, C., Andreescu, D., Patel, A., Goia, D., Andreescu, S. and Wallace, N., Toxicity and developmental defects of different sizes and shape nickel nanoparticles in Zebrafish. *Environmental Science & Technology*, Vol. 43, No 16, 2009, pp. 6349-6356
- Kang, G., Gillespie, P., Gunnison, A., Moreira, A., Wong, K. and Chen, L., Long-term inhalation exposure to nickel nanoparticles exacerbated atherosclerosis in a susceptible mouse model. *Environmental Health Perspectives*, Vol. 119, No 2, 2011 pp. 176-81
- Kobayashi, M., Expectation for "Nanotechnology Business Creation Initiative" in chemical industry. *Journal of Synthetic Organic Chemistry Japan*, Vol. 62, No 5, 2004, pp. 540-543
- Lademann, J., Weigmann, H. J., Rickmeyer, C., Barthelmes, H., Schaefer, H., Mueller, G. and Sterry, W., Penetration of titanium dioxide microparticles in a sunscreen formulation into the horny layer and the follicular orifice. *Skin Pharmacology and Applied Skin Physiology*, Vol. 12, No 5, 1999, pp. 247-256
- Lam, C. W., James, J. T., McCluskey, R. and Hunter, R. L., Pulmonary toxicity of single-wall carbon nanotubes in mice 7 and 90 days after intratracheal instillation. *Toxicological Sciences*, Vol. 77, No 1, 2004, pp. 126-134

- Lee, K. P., Kelly, D. P., Schneider, P. W. and Trochimowicz, H. J., Inhalation toxicity study on rats exposed to titanium tetrachloride atmospheric hydrolysis products for 2-years. *Toxicology and Applied Pharmacology*, Vol. 83, No 1, 1986, pp. 30-45
- Lee, K. P., Trochimowicz, H. J. and Reinhardt, C. F., Pulmonary Response of Rats Exposed to Titanium-Dioxide (TiO<sub>2</sub>) by Inhalation for 2 Years. *Toxicology and Applied Pharmacology*, Vol. 79, No 2, 1985, pp. 179-192
- Losch, A., Anticipating the futures of nanotechnology: visionary images as means of communication. *Technology Analysis & Strategic Management*, Vol. 18, No 3-4, 2006, pp. 393-409
- Lu, J. C., Jeng, S. L. and Wang, K. B., A review of statistical methods for quality improvement and control in nanotechnology. *Journal of Quality Technology*, Vol. 41, No 2, 2009, pp. 148-164
- Luther, W. F., Malanowski, N. and Zweck, A., Potentials of nanotechnology for economy, environment and enterprise. *Gaia-Ecological Perspectives for Science and Society*, Vol. 14, No 1, 2005, pp. 18-20
- Maynard, A., Baron, P., Foley, M., Shvedova, A., Kisin, E. and Castranova, V., Exposure to carbon nanotube material: Aerosol release during the handling of unrefined single walled carbon nanotube material. *Journal of Toxicology and Environmental Health*, Vol. 67, No 2004, pp. 87-107
- Mercer, R., Scabilloni, J., Wang, L., Kisin, E., Murray, A., Schwegler-Berry, D., Shvedova, A. and Castranova, V., Alteration of deposition pattern and pulmonary response as a result of improved dispersion of aspirated single walled carbon nanotubes in a mouse model. *American Journal of Physiology - Lung Cellular and Molecular Physiology*, Vol. 294, No 2008, pp. L87-L97
- Monica, J., ISO Publishes Nanotechnology Definition. *Nanotechnology Law Report*. Vol. No 2008., pp.
- Monteiro-Riviere, N., Nemanich, R., Inman, A., Wang, Y. and Riviere, J., Multi-walled carbon nanotube interactions with human epidermal keratinocytes. *Toxicology Letters* Vol. 155, No 3, 2005 pp. 377-384
- Moos, P. J., Chung, K., Woessner, D., Honeggar, M., Cutler, N. S. and Veranth, J. M., ZnO Particulate matter requires cell contact for toxicity in human colon cancer cells. *Chemical Research in Toxicology*, Vol. 23, No 4, 2010, pp. 733-739
- Morgan, D. M. L., Clover, J. and Pearson, J. D., Effects of synthetic polycations on leucine incorporation, lactate-dehydrogenase release, and morphology of human umbilical vein endothelial-cells. *Journal of Cell Science*, Vol. 91, No 1988, pp. 231-238
- Mossman, B. T. and Sesko, A. M., In vitro assays to predict the pathogenicity of mineral fibers. *Toxicology*, Vol. 60, No 1-2, 1990, pp. 53-61
- Muller, J., Huaux, F., Moreau, N., Misson, P., Heilier, J. F., Delos, M., Arras, M., Fonseca, A., Nagy, J. B. and Lison, D., Respiratory toxicity of multi-wall carbon nanotubes. *Toxicology and Applied Pharmacology*, Vol. 207, No 3, 2005, pp. 221-231
- Murray, A., Kisin, E., Kommineni, C., Kagan, V., Castranova, V. and Shvedova, A., Single-walled carbon nanotubes induce oxidative stress and inflammation in skin. *Toxicologist* Vol. 96, No 2007 pp. A1406
- Oberdorster, G., Ferin, J., Gelein, R., Soderholm, S. C. and Finkelshtein, J., Role of the alveolar macrophage in lung injury - studies with ultrafine particles. *Environmental Health Perspectives*, Vol. 97, No 1992, pp. 193-199
- Oberdorster, G., Ferin, J. and Lehnert, B. E., Correlation between particle-size, in-vivo particle persistence, and lung injury. *Environmental Health Perspectives*, Vol. 102, No 1994, pp. 173-179
- Oberdorster, G. and Yu, C. P., The carcinogenic potential of inhaled diesel exhaust - a particle effect. *Journal of Aerosol Science*, Vol. 21, No 1990, pp. S397-S401
- Oberdorster, G. and Yu, C. P., Commentary - Lung dosimetry - Considerations for non-inhalation studies. *Experimental Lung Research*, Vol. 25, No 1, 1999, pp. 1-6
- Poland, C., Duffin, R., Kinloch, I., Maynard, A., Wallace, W., Seaton, A., Stone, V., Brown, S., MacNee, W. and Donaldson, D., Carbon nanotubes introduced into the abdominal cavity of mice show asbestos-like pathogenicity in a pilot study. *Nature Nanotechnology* Vol. 3, No 2008, pp. 423 - 428
- Renwick, L. C., Brown, D., Clouter, A. and Donaldson, K., Increased inflammation and altered macrophage chemotactic responses caused by two ultrafine particle types. *Occupational and Environmental Medicine*, Vol. 61, No 5, 2004, pp. 442-447
- Ryman-Rasmussen, J., Riviere, J. and Monteiro-Riviere, N., Penetration of intact skin by quantum dots with diverse physicochemical properties. *Toxicological Sciences*, Vol. 91, No 1, 2006, pp. 159-165
- Saba, N., Samim, M. and Abidin, M., Concentration-dependent toxicity of iron oxide nanoparticles mediated by increased oxidative stress. *International Journal of Nanomedicine*, Vol. 5, No 1, 2010, pp. 983-989
- Sager, T. M., Kommineni, C. and Castranova, V., Pulmonary response to intratracheal instillation of ultrafine versus fine titanium dioxide: role of particle surface area. *Particle and Fibre Toxicology*, Vol. 5, No 2008, pp.
- Sahaym, U. and Norton, M. G., Advances in the application of nanotechnology in enabling a 'hydrogen economy'. *Journal of Materials Science*, Vol. 43, No 16, 2008, pp. 5395-5429
- Service, R. F., American Chemical Society meeting: nanomaterials show signs of toxicity. *Science*, Vol. 300, No 5617, 2003, pp. 243-243
- Shvedova, A., Kisin, E., Mercer, R., Murray, A., Johnson, V., Potapovich, A., Tyurina, Y., Gorelik, O., Arepalli, S., Schwegler-Berry, D., Antonini, J., Evans, D., Ku, B.-K., Ramsey, D., Maynard, A., Kagan, V., Castranova, V. and Baron, P., Unusual inflammatory and fibrogenic pulmonary responses to single walled carbon nanotubes in mice. *American Journal of Physiology - Lung Cellular and Molecular Physiology*, Vol. 289, No 2005, pp. L698-L708
- Shvedova, A., Kisin, E., Murray, A., Gandelsman, V., Maynard, A., Baron, P. and Castranova, V., Exposure to carbon nanotube material: assessment of the biological effects of nanotube materials using human keratinocyte cells. *Journal of Toxicology and Environmental Health*, Vol. 66, No 201, 2003, PP. 909-1926
- Shvedova, A., Kisin, E., Murray, A., Schwegler-Berry, D., Castranova, V., Kagan, V. E. and Tyurina, Y., Carbon nanotube exposure caused induction of oxidative stress, pulmonary injury and fibrosis. *Free Radical Research*, Vol. 40, No 2006, pp. S114-S114
- Takagi, A., Hirose, A., Nishimura, T., Fukumori, N., Ogata, A., Ohashi, N., Kitajima, S. and Kanno, J., Induction of mesothelioma in p53<sup>+/+</sup> mouse by intraperitoneal application of multi-wall carbon nanotube. *The Journal of Toxicological Sciences*, Vol. 33, No 1 2008, pp. 105-16
- Trouiller, B., Reliene, R., Westbrook, A., Solaimani, P. and Schiestl, R. H., Titanium dioxide nanoparticles induce DNA damage and genetic instability in vivo in mice. *Cancer Research*, Vol. 69, No 22, 2009, pp. 8784-8789
- Wang, B., Feng, W. Y., Wang, T. C., Guang, J., Wang, M., Shi, J. W., Zhang, F., Zhao, Y. L. and Chai, Z. F., Acute toxicity of

- nano- and micro-scale zinc powder in healthy adult mice. *Toxicology Letters*, Vol. 161, No 2, 2006, pp. 115-123
- Wang, J. X., Zhou, G. Q., Chen, C. Y., Yu, H. W., Wang, T. C., Ma, Y. M., Jia, G., Gao, Y. X., Li, B., Sun, J., Li, Y. F., Jiao, F., Zhao, Y. L. and Chai, Z. F., Acute toxicity and biodistribution of different sized titanium dioxide particles in mice after oral administration. *Toxicology Letters*, Vol. 168, No 2, 2007, pp. 176-185
- Warheit, D. B., Hoke, R. A., Finlay, C., Donner, E. M., Reed, K. L. and Sayes, C. M., Development of a base set of toxicity tests using ultrafine TiO<sub>2</sub> particles as a component of nanoparticle risk management. *Toxicology Letters*, Vol. 171, No 3, 2007, pp. 99-110
- Warheit, D. B., Laurence, B. R., Reed, K. L., Roach, D. H., Reynolds, G. A. M. and Webb, T. R., Comparative pulmonary toxicity assessment of single-wall carbon nanotubes in rats. *Toxicological Sciences*, Vol. 77, No 1, 2004, pp. 117-125
- Warheit, D. B., Reed, K. L. and Sayes, C. M., A role for surface reactivity in TiO<sub>2</sub> and quartz-related nanoparticle pulmonary toxicity. *Nanotoxicology*, Vol. 3, No 3, 2009, pp. 181-187